




## SEPARATING FLOOR



**SITE**  
**TEST ORGANISATION**  
**REPORT / TEST No. / TEST DATE**  
**TEST METHOD**  
**RESULTS**

Laboratory  
Sound Research Laboratories Ltd  
C/03/5L/0766/1 / Tests 3 and 4 / 8th August 2003  
BS EN ISO 140-4 and 7: 1998  
DnT,w (C ; Ctr) - 54 (-2 ; -7) dB  
DnT,w + Ctr - 47 dB  
L'nT,w (CI) - 57 (-0) dB

### FLOOR CONSTRUCTION

- 150mm precast concrete floor slabs (300kg/m<sup>2</sup>) built into cavity block walls on four sides.
- Joints between blocks and beams sealed with sand cement grout mix.
- Two layers of 5mm Ethafoam butt jointed and taped
- 40mm Gyvlon levelling screed applied over a polyethylene slip-sheet with a perimeter strip of 8mm polyethylene foam.
- A ceiling comprising 15mm standard grade (Type 1) plasterboard fixed to support channels at 400mm centres and a clear cavity of 75mm.

The results show that this floor system, as tested in conjunction with the associated constructions detailed above, is able to achieve the sound insulation performance required in the Building Regulations 2000, Approved Document E, 2003 Edition.

If this floor system were to be used on site with an equivalent construction and same build quality, similar results would be expected.

### BUILDING CONSTRUCTION DETAILS

Sound Research Laboratories Ltd. flanking transmission test laboratory at Holbrook House, Little Waldingfield, Sudbury, Suffolk. A two-storey purpose built test unit comprising cavity dense concrete block walls, a precast concrete first floor and a flat timber joist roof. Single rooms at ground and first floor level each approximately 25m<sup>3</sup> with a separating floor area of 10m<sup>2</sup>. Two leaves of 100mm dense concrete blocks with a 50mm cavity with wall ties at 600mm centres horizontally and 450mm vertically. 50mm Rockwool cavity closer (45kg/m<sup>3</sup>) running horizontally at the separating floor junction. Internal faces of block work finished with 12.5mm standard grade (Type 1) plasterboard fixed on plaster dabs.

LAFARGE GYVLON FLOWING SCREED  
ACOUSTIC TEST DATA SHEET - 04

Lafarge Gyvlon Ltd

Europa Boulevard, Westbrook Warrington WA5 7TN

Phone: 01925 428780 Fax: 01925 428788

Email: sales@gyvlon.co.uk

